



GPPS G3160 Padjam

PROPERTIES	TEST METHODS	TEST METHOD	UNITS	VALUES
General				
Density	-	ISO 1183	g/cm³	1,05
Bulk density	-	ISO 60	g/cm³	0, 55~0,65
ResidualMonomer	-	ISO	ppm	< 500
Rheological				
Melt flow rate	200°C - 5kg	ISO 1133	g/10'	2~3.5
Thermal				
Vicat softening temperature	10 N - 50°C/h	ISO 306/A	°C	>104