DESCRIPTION

EMDA-6200 grade is a high-density polyethylene copolymer resin designed for blow molding small to medium size bottles. It can be used on intermittent as well as continuous blow molding machines for high-speed production of high quality bottles. The bottles have excellent environmental stress cracking resistance and a good balance of rigidity and impact strength. They are easily trimmed and exhibit excellent surface attributes.

APPLICATIONS

EMDA-6200 is intended for producing containers of up to 10 liter capacity for packaging household and industrial chemicals (detergents, bleach, fabric softeners, etc.) toiletries, cosmetics and food products. It is also suitable for producing thin-walled parts and household items.

In addition EMDA-6200 can also be used successfully for extruding sheets and profiles including corrugated drainage pipes.

TYPICAL PROPERTIES

| Properties | Units | Test Method | Typical Value |
|---|-------------------|--------------------|------------------------|
| Resin Properties | | | 7.7 |
| Melt Index, I _{2.16} | g/10 min | ASTM D 1238 | 0.4 |
| High Load Melt Index, I _{21.6} | g/10 min | ASTM D 1238 | 33 |
| Density | g/cm ³ | ASTM D 1505 | 0.955 |
| Thermal Properties | | | |
| Vicat Softening Temperature | °C | ASTM D 1525 | 125 |
| Deflection Temperature (445 KPa Load) | °C | ASTM D 648 | 70 |
| Melting Point | °C | EQUATE | 135 |
| Crystallization Point | °C | EQUATE | 112 |
| Coefficient of Linear Expansion | cm/cm/°C | ASTM D 696 | 1.2 x 10 ⁻⁴ |
| Mechanical Properties | | | |
| Tensile Strength at Yield | MPa | ASTM D 638 | 27 |
| Ultimate Tensile Elongation | % | ASTM D 638 | 730 |
| Flexural Modulus | MPa | ASTM D 790 | 1350 |
| Brittleness Temperature | °C | ASTM D 746 | <-100 |
| $ESCR^+, F_{50}$ | Hours | ASTM D 1693 B | 50 |
| Bottle* Properties | | | |
| Top Crushing Load at Failure, 23°C | Kg | ASTM D 2659 | 50 |
| Drop Impact, Mean Failure Height | m | ASTM D 2463 | 4.3 |

⁺ Environmental Stress Cracking Resistance

ASTM - American Society for Testing and Materials

TYPICAL MOLDING CONDITIONS

| Molding Temperatures | for Intermittent Mac | nines | |
|-----------------------------|----------------------|---------|--|
| Barrel Zone 1, °C | | 175-180 | |
| Barrel Zone 2-4, °C | | 185-190 | |
| Head and Die, °C | | 185-190 | |
| Melt Temperature, °C | | 200-215 | |
| Molding Temperature | for Continuous Machi | nes | |
| Barrel Zone 1, °C | | 175-180 | |
| Barrel Zone 2-4, °C | | 185-190 | |
| Head and Die, °C | | 185-190 | |
| Adapter, °C | | 185-190 | |
| Melt Temperature, °C | 90 RPM | 215 | |
| - | 130 RPM | 220 | |

FOOD CONTACT USAGE

EMDA-6200 can be used for all food contact applications including holding food during cooking. It conforms to US FDA Regulation 21 CFR 177.1520 as well as EC Directive 90/128/EEC and its amendments to-date. Food contact suitability certificate is available upon request.

AVAILABILITY

EMDA-6200 is supplied in 25-Kg bags in secured pallets of 55 bags (1.375 MT net). It is also supplied in sea bulk containers of up to 15 MT capacity.

^{* 41}g Boston Round quart (0.946 liter) bottle